



TEST REPORT TUCHENG

ORIGINAL

Date of Issue: Feb. 22, 2023 Date of Receipt and Test Start: Feb. 17, 2023

Report No.: TPF2B228 Quantity: 1PC Page Order/Pages: (P1/1) Ref. No.: NIL


Report Title: Steady Flying Enterprise Co., Ltd.(T4799) Item: Woven Fabric

Address: 1f, No. 2-1, Alley 30, Lane 358, Ruiguang Rd., Neihu District, Taipei City 114-92, Taiwan(R.O.C.)

Test Items	Test Results		Test Methods
Yarn Number as Received	Warp	1129 D	CNS 12915 L3233-2010
	Filling	1009 D	6.8.1
Fabric Count (ends/inch)	Warp wise	36.0	CNS 12915 L3233-2010 6.6
	Filling wise	30.0	Environmental Condition: 20°C, 65%RH

Note: Sample description is given by the client: 1000D high-tenacity yarn Nylon

Note: As the remaining sample was asked to return along with the test report, re-testing would not be possible.



- Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.
- 2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- 3.The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Jui-hung kao
Taiwan Textile Research Institute

Director,
Department of Testing and Certification
Department of Testing and Certification, Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)
Tel : +886-2-22670321 ext. 7107, 7110
Fax : +886-2-22675108 , +886-2-22689839



試驗報告 土城場區
TEST REPORT TUCHENG

正 本
ORIGINAL

發行日期 2023.02.22 收件/試驗起始日期 2023.02.17
Date of Issue: 2023.02.22 Date of Receipt and Test Start: 2023.02.17

報告編號 TPF2B228 數量 1件 報告頁次/頁數 (P1/1) 來文字號 空 白
Report No.: TPF2B228 Quantity: 1 Page Order/Pages: (P1/1) Ref. No.:



報告抬頭 翔穩企業有限公司(T4799) 試件類別 梭織布
Report Title: 翔穩企業有限公司(T4799) Item: 梭織布

地址 114 台北市內湖區瑞光路358巷30弄2之1號1樓
Address: 114 Taipei City, Neihu District, Ruiguang Road 358 Alley 30 Lane 2 No. 1-1

試驗項目		試驗結果	試驗方法
現狀支數	經紗	1129 D	CNS 12915 L3233-2010
	緯紗	1009 D	6.8.1
密度 (根/吋)	經向	36.0	CNS 12915 L3233-2010 6.6
	緯向	30.0	環境條件: 20°C, 65%RH

註: 依委託者所提供來樣資料為: 1000D 強力紗尼龍胚布

註: 試餘樣品應委託人要求已隨本報告退還不再接受檢驗。



- 附記: 1.本報告僅對樣品負責, 樣品保留期限為一個月。
Note: This report is only responsible for the submitted sample(s), which will be kept for one month period.
2.本報告非經本檢測及驗證部書面同意, 不得摘錄複製, 但全部複製除外。
This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
3.試驗報告所載事項不得作為公開廣告及商業推銷之用。
The test report should not be used for public advertisement and commercial promotion.

財團法人紡織產業綜合研究所
授權核發人:
Authorized by president of
Taiwan Textile Research Institute

紡織產業綜合研究所檢測及驗證部 新北市土城區承天路6號
Department of Testing and Certification, Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)
Tel : +886-2-22670321 ext. 7107, 7110
Fax : +886-2-22675108 , +886-2-22689839