



**TEST REPORT TUCHENG**

ORIGINAL

Date of Issue: Feb.17,2023 Date of Receipt and Test Start: Feb.09,2023

Report No.: TAF2B117 Quantity: 1PC Page Order/Pages: (P1/1) Ref. No.: NIL  
Steady Flying Enterprise Co., Ltd.(T4799) Coated Fabric

Report Title: \_\_\_\_\_ Item: \_\_\_\_\_  
Address: 1f, No. 2-1, Alley 30, Lane 358, Ruiguang Rd., Neihu District, Taipei City 114-92, Taiwan(R.O.C.)

Test Items		Test Results		Test Methods
Color F. Crocking (Grade)	Dry	Warp wise	4	CNS 1499 L3032-2008 Type I
		Filling wise	4	
	Wet	Warp wise	4	
		Filling wise	4	
Colorfastness to Light (Grade)		3-4		CNS 3845 L3074-1998
Fabric Structural Analysis		Plain		CNS 12915 L3233-2010 6.1
Breaking Strength (kgf/5cm)	Warp wise	441.0		CNS 12915 L3233-2010 6.12.1(1)Strip Method Speed:20± 1cm/min,CRE
	Filling wise	347.4		
Tearing Strength (kgf)	Warp	35.9		CNS 12915 L3233-2010 6.15.1 Single tongue Method Speed:15± 1cm/min,CRE specimen width:5cm
	Filling	31.4		

Note: "5cm"of the unit of Breaking Strength is the wide of test specimen.

Note: Sample description is given by the client: 1000D 100% Nylon-DCT (Coated Fabric)

Note: As the remaining sample was asked to return along with the test report, re-testing would not be possible.



Authorized by president of  
Department of Testing and Certification, Textile Research Institute

*Jui-hung Kao*

Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.

2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.

3.The test report should not be used for public advertisement and commercial promotion.

**Director,**  
**Department of Testing and Certification,**  
Department of Testing and Certification, Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108 , +886-2-22689839



試驗報告 土城場區  
TEST REPORT TUCHENG

副本  
COPY

發行日期 Date of Issue: 2023.02.17 收件/試驗起始日期 Date of Receipt and Test Start: 2023.02.09

報告編號 Report No.: TAF2B117 數量 Quantity: 1件 報告頁次/頁數 Page Order/Pages: (P1/1) 來文字號 Ref. No.: 空白

報告抬頭 Report Title: 翔穩企業有限公司(T4799) 試件類別 Item: 塗佈布

地址 Address: 114 台北市內湖區瑞光路358巷30弄2之1號1樓

試驗項目		試驗結果		試驗方法
耐摩擦牢度 (級)	乾	經向	4	CNS 1499 L3032-2008 I 型
		緯向	4	
	濕	經向	4	
		緯向	4	
耐光牢度 (級)		3-4		CNS 3845 L3074-1998
織物組織		平紋		CNS 12915 L3233-2010 6.1
斷裂強力 (kgf/5cm)	經向	441.0		CNS 12915 L3233-2010 6.12.1(1)條式法 速度:20±1cm/min,CRE
	緯向	347.4		
撕裂強力 (kgf)	經紗	35.9		CNS 12915 L3233-2010 6.15.1 單舌片甲法 速度:15±1cm/min,CRE 試樣寬度:5cm
	緯紗	31.4		


註：斷裂強力測試結果單位之5cm表示試樣寬度。

註：依委託者所提供來樣資料為：1000D 尼龍布-DCT (國軍數位迷彩)

註：試餘樣品應委託人要求已隨本報告退還不再接受檢驗。



財團法人紡織產業綜合研究所  
所長授權核發人：  
Authorized by president of  
Taiwan Textile Research Institute



附註: 1.本報告僅對樣品負責,樣品保留期限為一個月。  
Note: This report is only responsible for the submitted sample(s), which will be kept for one month period.  
2.本報告非經本檢測及驗證部書面同意,不得摘錄複製,但全部複製除外。  
This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.  
3.試驗報告所載事項不得作為公開廣告及商業推銷之用。  
The test report should not be used for public advertisement and commercial promotion.

紡織產業綜合研究所檢測及驗證部 新北市土城區承天路6號  
Department of Testing and Certification, Taiwan Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108, +886-2-22689839