

TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : HL80013A/2014

Page : 1 of 2

Date : AUG. 11, 2014

J-TECH TACTICAL GEAR LIMITED

1F, No. 2-1 Alley 30, Lane 358, Ruiguang Rd, Neihu District, Taipei City, 114, Taiwan, R.O.C.

The following merchandise was submitted and identified by the applicant as:

Product Description: 550 Parachute Cord
Style/Item No.: TA05-0203-00
Manufacturer/Vendor: J-TECH TACTICAL GEAR LIMITED
Country of Origin: Taiwan

We have tested the submitted sample as requested and the following results were obtained:

Test Requested: Pulling Test

Test Method:

1. Secure the sample on the testing machine. (As shown in photo B)
2. Apply an upward force to the sample until it is damaged .
3. Record any findings and maximum pulling force.
4. Testing Machine: INSTRON 5581, Rate: 100 mm/min.

Test Result:

Sample	Max. pulling force (kgf)	Result
550 Parachute Cord	468.8	The sample was broken after testing. (As shown in photo C)




Date of Receipt: Aug. 01, 2014

Testing Period: Aug. 01, 2014 ~ Aug. 11, 2014

Signed for and on behalf of
 SGS Taiwan Ltd.

Jackson Chen
 Jackson Chen
 Team Leader

– Picture(s)–

	
<p>Photo A : Appearance of the sample</p>	<p>Photo B : Test setup</p>
	<p>---</p>
<p>Photo C : After testing</p>	<p>---</p>

---End of Report---

