

## TEST REPORT

Mechanical & Hardgoods Laboratory

Report No.: HL70344A/2015

Page: of

JUL. 28, 2015 Date:

## J-TECH TACTICAL GEAR LIMITED

1F, No. 2-1 Alley 30, Lane 358, Ruiguang Rd, Neihu District, Taipei City, 114, Taiwan, R.O.C.

The following merchandise was submitted and identified by the applicant as:

Product Description:

1 3/4" EMERGENCY RESCUE RIGGER BELT-Webbing

Style/Item No.:

TA01-0107-00

Manufacturer/Vendor:

J-TECH TACTICAL GEAR LIMITED

Country of Origin:

Taiwan

We have tested the submitted sample as requested and the following results were obtained:

Test Requested:

Pulling Test (Refer clause 7.2.1 Standard conditioning for performance test of

CNS 3972)

Test Method:

- Secure the sample on the testing machine. (As shown in photo B)
- Apply an upward force to the sample until it is damaged and record maximum pulling force.
- 3. Testing Machine: INSTRON 5581, Rate: 100 mm/min, Gauge: 200 mm

Test Result:

lest Result:		
Sample	Max. pulling force (kgf)	Result G E A
1 3/4" EMERGENCY RESCUE RIGGER BELT-Webbing	3685.5	The sample was damaged after testing. (As shown in photo C)

Date of Receipt:

Jul. 20, 2015

Testing Period:

Jul. 20, 2015 ~ Jul. 28, 2015

Signed for and on bel SGS Taiwan Ltd

Jackson Chen Team Leader

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any, The Company's sole responsibility is to its Client and this document does not exponente parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested

No.127, Wu Kung Road, New Taipei Industrial Park, New Taipei City, Taiwan /新光市新先產業園區五工路 127 號

台灣檢驗科技股份有限公司

t (886-2) 2299-3279

f (886-2) 2299-2920

www.tw.sgs.com Member of SGS Group




## TEST REPORT

Mechanical & Hardgoods Laboratory

Report No.: HL70344A/2015

Page: of

- Picture(s)-



---End of Report---



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Termsshown in this test report refer only to the sample(s) tested SGS Taiwan Ltd.

No.127, Wu Kung Road, New Taipei Industrial Park, New Taipei City, Taiwan /新光市新北產當園医五工路 127 號

台灣檢驗科技股份有限公司

f (886-2) 2299-2920 t (886-2) 2299-3279 www.tw.sgs.com